

## ARGOREV TEMATIZACIÓN

Thixotropic mortar for the realisation of reliefs



### Colors:



**Brown**  
24.5Kg - 350079



**White**  
24.5Kg - 350078

ARGOREV TEMATIZATION is a mortar based on hydraulic binders, selected aggregates, organic additives and special fibres that give it an extraordinary thixotropy that allows moulding, sculpting, moulding and stamping.

### Presentation

- Appearance: Powder
- Colour: Brown
- Weight (kg): 24.5
- Product code: 350079

### Technical Data

Concept	Value	Standard
Mass per unit area (nominal) (kg/m <sup>2</sup> )	25	-
Mixing water (%)	22	-
Classification according to UNE EN 998-1	CR CSIV W2	-
Thermal conductivity declared (W/mK)	0.67	-
Bulk density (kg/L)v ~ Value	1.40	-

Concept	Value	Standard
Maximum thickness (mm)	40	-
Minimum thickness (mm)	5	-
Grain size range (mm) ~ value	0/1	-
Reaction to fire	A1	-

## Scope

- Indoor and outdoor.
- Realization of coatings on facades on ceramic enclosure.

## Advantages & Benefits

- Waterproofed
- Waterproof to rain water.
- Permeable to water vapour.
- Projectable.
- Without off-hook.
- Thixotropic.
- Direct application on masonry.
- Colour chart.
- Lightened.

## Descriptive Memory

The work of execution of the relief and its theming will be carried out with the dry mortar ARGOREV® TEMATIZATION, from the company DANOSA, of class CR (CSIV) W2 according to the UNE EN 998-1 standard. The substrate must be sound, clean, free of friable parts, completely hardened and have completed its time of dimensional variation. The construction joints shall be respected.

## Support

- (On concrete and other super-absorbent or non-absorbent substrates, apply a suitable primer).
- Brick or ceramic block factory.
- Brick.

## Substrate preparation

- In case of heat, wind or on very absorbent substrates, it is advisable to dampen the substrate and wait for the water film to disappear.
- Do not apply on plasters or paints.
- The support must be healthy, clean, flat, free of paint, crumbling or poorly adhered parts, release agents, etc. and in general without any substance or particle that may prevent correct adherence.

## Instruction for Use

- Mix ARGOREV® TEMATIZATION with approx. 5.5 L of clean water per 25 kg bag manually or mechanically until a homogeneous, creamy and lump-free mixture is obtained.
- Spread the mortar leaving an average thickness of between 5-40 mm. and smooth the applied material to even out the thicknesses and smooth the surface.
- Once the hardening process has begun, proceed to mould the material with the appropriate tools (trowels, spatulas, blades, etc.).
- Once hardened, sand and sculpt the desired parts and pigment if necessary.

## Warning

- Store in a dry place, protected from rain, sun, high and low temperatures.
- It is advisable to mesh the application at singular points.
- When applied at very high relative dampness, drying may be delayed.
- In case of splashes in the eyes, rinse with plenty of water and seek medical attention if necessary. For more detailed information see safety data sheet.
- Do not apply when there is a risk of rain or frost.
- Do not add more water once it has started to set.
- Comply with the mixing water.

## Handling, storage and preservation

- It is packaged in 25 kg multi-leaf paper bags with damp-proof sheets that allow it to be stored for 12 months in its original sealed packaging, safe from dampness.

## Safety and hygiene

- Consult the safety data sheet.

## Notice

- The information contained in this document and any other advice provided, are given in good faith, based on DANOSA's current knowledge and experience when products are properly stored, handled and applied, in normal situations and in accordance with the recommendations of DANOSA. The information applies only to the application (s) and the product (s) to which reference is expressly made. In case of changes in the parameters of the application, or in case of a different application, consult the DANOSA Technical Service before using the DANOSA products. The information contained herein does not exonerate the responsibility of the building agents to test the products for the application and intended use, as well as their correct application in accordance with current legal regulations. The product images used in our communications are indicative and may differ slightly in color and aesthetic appearance in relation to the final product. Orders are accepted in accordance with the terms of our current General Sales Conditions. DANOSA reserves the right to modify, without prior notice, the data reflected in this documentation. Website: **www.danosa.com** E-mail: **info@danosa.com** Telephone: **+34 949 88 82 10**