

ARGOTEC REPARACION R3

Concrete structural repair mortar



ARGOTEC REPARACIÓN R3 is a thixotropic polymer modified mortar (PCC), single-component, high-strength and non-shrink, for structural repair of concrete elements, formulated with a mixture of hydraulic binders, selected aggregates, polymers, corrosion inhibitors and fibres that provide excellent adhesion and mechanical properties.

Presentation

- Appearance: Powder
- Colour: Grey
- Weight (kg): 25
- Yield (kg/m²): 18 kg/m² y cm de espesor
- Performance in mm thickness (kg/m²): 1,8
- Product code: 350142

Technical Data

Concept	Value	Standard
Mass per unit area (nominal) (kg/m ²)	25	-
Capillary Absorption (kg/m ² h ^{0.5})	W2 (0,2)	-
Classification according to UNE EN 1504-3	R3 (PCC)	-
Thermal compatibility. Part I. (N/mm ²)	2	-
Thermal conductivity declared (W/mK)	1	-
Chloride ion content (%)	0.05	-
Bulk density (kg/L)v ~ Value	1,50 ± 0,16	-

Concept	Value	Standard
Fresh mass density (kg/L) ~ Value	1,80 ± 0,16	-
Maximum thickness (mm)	30	-
Minimum thickness (mm)	10	-
Water vapour permeability (m)	Clase I	-
Reaction to fire	A1	-
Compacting resistance 24 hours (N/mm ²)	≥ 10	-
Compacting resistance 28 days (N/mm ²)	≥ 30	-
Compacting resistance 7 days (N/mm ²)	≥ 20	-
Resistance to carbonation	Pasa	-
Retraction at 28 days (mm/m)	≤ 0,1	-
Hazardous substances	Ver HS	-
Application time (min)	30	-
Mixture lifetime (min)	30	-

Additional Technical Data

Concept	Value	Standard
CO2 permeability	Clase III	-

Scope

- Conservation and restoration of coats. Principle 7. Methods 7.1 and 7.2.
- Repair of prefabricated elements.
- Repair and regeneration of structural and non-structural elements.
- Structural concrete reinforcement works. Principle 4. Method 4.4.
- Concrete repair work. Principle 3. Methods 3.1 and 3.3.
- Repair work on edges, cornices, balcony edges and roofs.

Advantages & Benefits

- Outstanding Adhesion
- Excellent workability.
- Free of chlorides.
- Made of sulphur-resistant cement.
- Rapid development of resistance.

- Fast drying.
- No retraction.
- Thixotropic.
- Made with corrosion inhibitor.

Descriptive Memory

The repair of concrete elements will be carried out with ARGOTEC REPARACIÓN R3 mortar, from the Argos cement derivatives company, class R2 according to the UNE EN 1504-3 standard, in accordance with principle 3 (methods 3.1 and 3.3), principle 4 (method 4.4.) or principle 7 (methods 7.1. and 7.2.). The fixing substrate shall be sound, clean, free of friable parts, fully hardened and have completed its time of dimensional variation. The construction joints shall be respected.

Support

- Precast concrete elements.
- Concrete structures.

Substrate preparation

- In any case, the specific requirements of EN 1504-10 must be taken into account.
- Metal elements, such as reinforcement, must be free of rust, dust, mortar residues or other materials that may impede adhesion or contribute to corrosion.
- Absorbent substrates must be wetted to saturation without puddling.
- The substrates must be clean and sound, free of grease, paint or other substances that would prevent proper adhesion.
- Very smooth substrates shall be mechanically treated to ensure proper adhesion of the mortar.
- A suitable adhesion primer shall be used on low-porosity surfaces.

Instruction for Use

- Mix ARGOTEC REPARACIÓN R3 with 3.75-4.25 L of clean water per 25 kg bag, preferably by mechanical means, until a homogeneous, creamy, lump-free mixture is obtained.
- Apply the mortar manually with the trowel in thicknesses never less than 10 mm. nor more than 30 mm. pressing the mortar with the trowel on the substrate.
- The application time is approximately 30 minutes depending on the environmental conditions.

Warning

- Do not apply when there is a risk of frost, rain, strong wind or direct sunlight.
- Do not apply below 5°C or above 30°C.
- Do not apply on plaster supports.
- Do not apply to plastic, wood, rubber, etc. surfaces.
- Protect the cool surface from direct sun, rain and especially draughts.

Handling, storage and preservation

- It is packaged in 25 kg multi-leaf paper bags with damp-proof sheets and in 5 kg plastic bags that allow it to be stored for 12 months in its original sealed packaging, safe from dampness.

Cleaning of Work Tools

- Fresh product, with water
- Dry product, scratching

Notice

- The information contained in this document and any other advice provided, are given in good faith, based on DANOSA's current knowledge and experience when products are properly stored, handled and applied, in normal situations and in accordance with the recommendations of DANOSA. The information applies only to the application (s) and the product (s) to which reference is expressly made. In case of changes in the parameters of the application, or in case of a different application, consult the DANOSA Technical Service before using the DANOSA products. The information contained herein does not exonerate the responsibility of the building agents to test the products for the application and intended use, as well as their correct application in accordance with current legal regulations. The product images used in our communications are indicative and may differ slightly in color and aesthetic appearance in relation to the final product. Orders are accepted in accordance with the terms of our current General Sales Conditions. DANOSA reserves the right to modify, without prior notice, the data reflected in this documentation. Website: **www.danosa.com** E-mail: **info@danosa.com** Telephone: **+34 949 88 82 10**