danosa

Ancillaries

# DANOMAT 100 REINFORCEMENT

Fiberglass mat for reinforcement of waterproof elastic coatings

Fiberglass mat for reinforcement of waterproof elastic coatings

## Presentation

- Length (cm): 5000
- Width (cm): 100
- Weight (kg): 8
- Surface (m²): 50
- Product code: 770050

## Technical Data

| Concept | Value | Standard |
|---|---|---|
| Humedad (%) | ≤ 0,2 | - |
| **Concept** / **Value** / **Standard** | | |
| Grammage (g/m²) / 45 ± 5 / - | 100 | - |
| Longitudinal & transversal tensile strength (N/5cm) / Urdimbre: ≥ 750-900 Trama: ≥ 450-600 / - | | |
| Resin content (%) / 13 - 18 / - | | |
| Tensile strength (N/mm²) | ≥ 80 | - |

## Scope

- At 90° angles reinforcing the first layer of waterproofing coatings

- Reinforcement of cladding on vertical supports and at singular points, reducing the risk of cracking.

## Advantages & Benefits

- Easy to apply, no mechanical fixing required.
- Extends the durability of coatings
- Reduces the risk of cracking.
- Good and fast wetting in resins, rapid air release.
- High mechanical strength of the parts.
- Very high resistance to acid corrosion.

## Warning

- The handling of this product does not require special care. However, it may cause irritation on sensitive skin. In this case, wash with soap and cold water.

## Notice

- The information contained in this document and any other advice provided, are given in good faith, based on DANOSA's current knowledge and experience when products are properly stored, handled and applied, in normal situations and in accordance with the recommendations of DANOSA. The information applies only to the application (s) and the product (s) to which reference is expressly made. In case of changes in the parameters of the application, or in case of a different application, consult the DANOSA Technical Service before using the DANOSA products. The information contained herein does not exonerate the responsibility of the building agents to test the products for the application and intended use, as well as their correct application in accordance with current legal regulations. The product images used in our communications are indicative and may differ slightly in color and aesthetic appearance in relation to the final product.Orders are accepted in accordance with the terms of our current General Sales Conditions.DANOSA reserves the right to modify, without prior notice, the data reflected in this documentation.Website: **www.danosa.com** E-mail: **info@danosa.com** Telephone: **+34 949 88 82 10**