

DANOPUR PT

Liquid membrane for waterproofing and protection of pedestrian walkable roofs



Single-component, cold-applied, seamless, elastic, moisture-reactive, easily applied, polyurethane liquid membrane used for waterproofing.

Presentation

- Colour: Grey
- Weight (kg): 25
- Logistic class: (C) Products usually in stock, maximum availability in less than 7 days
- Product code: 750705

Technical Data

Concept	Value	Standard
Adhesion to concrete (N/mm ²)	> 2,0 (con imprimación)	ASTM D903
Dureza (Shore A)	65 - 70	ASTM D2240
Elongation at break (%)	> 600	-
Tensile strength (N/mm ²)	> 4	ASTM D412
Punteo de fisuras (mm)	> 2 (-10oC)	EOTA TR-008
Resistencia a la presión del agua (1 m.c.a. 24h)	No filtra (1m columna de agua, 24h)	DIN EN 1928
Resistencia a la radiación de calor	Superado	DIN 4102-7
Temperatura de servicio (°C)	-30 a + 90	-

Concept	Value	Standard
Tiempos de secado (23°C y 50% HR). Curado total (días)	7	-
Tiempos de secado (23°C y 50% HR). Tiempo de estabilidad con lluvia (horas)	3 - 4	-
Drying times (23°C and 50% RH). Final drying time (days)	7	-
Tiempos de secado (23°C y 50% HR). Tiempo para tránsito de personas (horas)	18 - 24	-
Transmisión de vapor de agua (g/m ² /día)	30	ISO 9932:91

Additional Technical Data

Concept	Value	Standard
Adhesion to concrete (N/mm ²)	> 2,0 (con imprimación)	ASTM D903
Resistencia a la presión del agua (1 m.c.a. 24h)	No filtra (1m columna de agua, 24h)	DIN EN 1928

Scope

- Waterproofing of balconies and terraces.
- Roof waterproofing.
- Waterproofing of surfaces with complicated geometries
- Waterproofing in wet areas such as bathrooms, kitchens, terraces (under tiles).
- Waterproofing and renovation of roofs with asphalt sheets and old acrylic sheets.
- Polyurethane foam protection and coating.

Advantages & Benefits

- High elasticity >600% and crack bridging.
- Good chemical resistance to oils, salt water, domestic detergents, alkaline and acid solutions (5%).
- Excellent bonding.
- Excellent resistance to extreme temperatures -30°C to + 90°C.
- Easy cold application.
- Continuous seamless waterproof membrane.
- Permeable to water vapour.
- Resistant to water and ice.
- Resistant to pedestrian traffic.

Support

- Aluminium
- Tiles
- Polyurethane foam
- Asbestos cement

- Concrete
- Mortar
- Asphalt sheets
- Acrylic membranes
- Zinc

Instruction for Use

- **Application method:** Apply DANOPUR® BALCONIES by roller or airless, in one or two coats. 3-5 hours drying time between each coat (no more than 6 hours). For a correct result, the temperature during application and curing should be between 5 and 35°C. Humidity may affect the final result.
- **Total consumption:**

Waterproofing: 1.3 to 2.5 kg/m² applied in two or three coats. **Tools:** Roller, brush, rubber trowel or airless spraying equipment. **Checking environmental conditions:** Ambient/substrate temperature between 5 to 35°C. Relative humidity < 80%. Waterproofing work must not be carried out when weather conditions may be detrimental (when it is snowing or there is snow or ice on the roof; when it is raining or the roof is wet). **Product preparation:** Stir for at least 1 minute with a mechanical stirrer until homogeneous mixture is obtained.

Membrane application: A coat of DANOPRIMER® primer must be applied according to the type of substrate to promote adhesion of the membrane. Respecting the curing times of the primer, apply three coats of DANOPUR® PT. Always reinforce the singular points, such as vertical and horizontal wall junctions, areas where the substrate changes, junctions with drains, etc. It is recommended to reinforce the entire surface with PET50 polyester reinforcement (the overlap of this reinforcement should be between 5 and 10 cm) and leave it to soak into the first layer, still in a damp state, and then apply the PET50 reinforcement (the overlap of this reinforcement should be between 5 and 10 cm). After a minimum of 12 hours and a maximum of 48 hours apply the second coat of DANOPUR® PT and for more demanding end-use roofs apply a third coat of DANOPUR® PT. Do not apply coats thicker than 0.6 mm. If a colourfast finish is desired, apply one or two coats of DANOPUR® LT over the DANOPUR® PT membrane. DANOPUR® PT is slippery when wet. To avoid this, it is recommended to sprinkle DANOQUARTZ SP49 silica aggregate on the last coat of the system to achieve a slip resistant surface. DANOPUR® PT is not recommended for use in direct contact with treated or chlorinated water.

Warning

- Consult the safety data sheet.
- Contains isocyanates.
- Dispose of contents/container with all possible precautions.
- Read the label before use.
- Do not apply layers thicker than 0.6 mm.
- Waterproofing work must not be carried out when weather conditions may be detrimental, in particular in situations of snow, ice, rain or strong wind.
- Slippery if wet. To avoid this, spread suitable aggregates on the still-wet membrane to achieve a slip-resistant surface.
- If a colourfast finish is desired, apply one or two coats over the DANOPUR® PT membrane.

Handling, storage and preservation

- 9 months.
- The container must be stored upside down, with the lid resting on the shelf or support.

Cleaning of Work Tools

Cleaning diluent. Clean all application tools and equipment immediately after use with diluent.

Notice

- The information contained in this document and any other advice provided, are given in good faith, based on DANOSA's current knowledge and experience when products are properly stored, handled and applied, in normal situations and in accordance with the recommendations of DANOSA. The information applies only to the application (s) and the product (s) to which reference is expressly made. In case of changes in the parameters of the application, or in case of a different application, consult the DANOSA Technical Service before using the DANOSA products. The information contained herein does not exonerate the responsibility of the building agents to test the products for the application and intended use, as well as their correct application in accordance with current legal regulations. The product images used in our communications are indicative and may differ slightly in color and aesthetic appearance in relation to the final product. Orders are accepted in accordance with the terms of our current General Sales Conditions. DANOSA reserves the right to modify, without prior notice, the data reflected in this documentation. Website: **www.danosa.com** E-mail: **info@danosa.com** Telephone: **+34 949 88 82 10**