

### GLASDAN 40 P ELAST

SBS elastomeric 4 kg/m<sup>2</sup> underlay.  
Torch applied.



GLASDAN 40 P ELAST. is a waterproofing bituminous sheet with non self-protected surface of 4.0 kg/m<sup>2</sup>. Composed of a fibreglass reinforcement and covered on both sides with SBS modified bitumen mastic. A polyethylene film is used as anti-adherent material on both sides. Tested according to standard EN test methods.

#### Presentation

- Length (cm): 1000
- Width (cm): 100
- Thickness (mm): 3.3
- Product code: 141031

#### Technical Data

Concept	Value	Standard
Mass per unit area (nominal) (kg/m <sup>2</sup> )	4	-
External fire behaviour	Broof(t1)	UNE-EN 1187; UNE-EN 13501-5
Durability flexibility	-5 ± 5	-
Creep durability (°C)	100 ±10	UN-EN 1110
Elongation at break longitudinal (%)	PND	UNE-EN 12311-1
Elongation at transverse break (%)	PND	UNE-EN 12311-1
Water vapour resistance factor (μ)	20.000	UNE-EN 1931
Low temperature flexibility (°C)	<-15	UNE-EN 1109

Concept	Value	Standard
Reaction to fire	E	UNE-EN 11925-2; UNE-EN 13501-1
Resistance to static loading (kg)	PND	UNE-EN 12730
Resistance to root penetration	No pasa	UNE-EN 13948
Longitudinal tensile strength (N / 5cm)	500 ± 100	UNE-EN 12311-1
Transverse tensile strength (N / 5cm)	400 ± 100	UNE-EN 12311-1
Longitudinal resistance to tearing (nail shank) (N)	PND	UNE-EN 12310-1
Transversal resistance to tearing (nail shank) (N)	PND	UNE-EN 12310-1
Resistance to impact, A (mm)	PND	UNE-EN 12691
Joint Strength: Welding Shear	400 ± 100	UNE-EN 12317-1
Hazardous substances	PND	-
Resistance to root penetration	No pasa	UNE-EN 13948

## Additional Technical Data

Concept	Value	Standard
Density (kg/m³)	1212	-
Adhesion of granules (%)	PND	UNE-EN 12039
Creep resistance at high temperatures (°C)	>100	UN-EN 1110

## Environmental Information

Concept	Value	Standard
Post-consumer recycled content (%)	35	-
Manufactured in	Fontanar - Guadalajara (España)	-

## Standards and Certification

- In accordance with the UNE-EN 13707 standard 'Flexible sheets for waterproofing - Reinforced bitumen sheets for roof waterproofing - Definitions and characteristics'.
- Complies with CE marking requirements.
- DIT 569R/16 "POLYDAN TRAFFIC ROLLED".
- DTA 5/09-2088 "Glasdan ELAST-Esterdan ELAST-Polydan ELAST".

## Scope

- Bottom or top sheet in two-layer membranes for waterproofing of roofs with heavy bonded protection.
- Bottom or top sheet in two-layer membranes for waterproofing of heavy unbonded or floating roofs with heavy protection.
- Bottom reinforcement in improved single-ply waterproofing membranes for roof waterproofing with heavy bonded protection.
- Bottom reinforcement in improved single-ply waterproofing membranes for waterproofing of heavy unbonded or floating roofs with heavy protection).

## Advantages & Benefits

- Little thermal variation.
- High dimensional stability.
- The sheet, being made of a bitumen mastic modified with SBS-type elastomeric polymers, substantially improves other bituminous mastics, providing much better performance in terms of reaction at high and low temperatures, elasticity and resistance to ageing, which leads to greater durability of the sheet and greater safety of the waterproofing membrane.
- Limits deformations.
- Limits stresses in the waterproofing membrane.
- Very good performance in multilayer systems with hot asphalt.
- Allows for adaptation to any type of geometry.
- Allows for working with molten asphalt.

## Instruction for Use

The POLYDAN 50/GP ELAST. GREEN GARDEN (5 m) is laid over the first layer in the same direction, and fully bonded. The top layer is installed with side laps a minimum of 60 mm and end laps 100 mm wide. Laps between the membrane and any base sheets should be offset by a minimum of 300 mm. Bonding is achieved by melting the lower surface by torching and pressing the membrane down. Care must be taken not to overheat the membrane. It is imperative that the drainage system of the green roof or roof garden is designed correctly, and provision is made for access for maintenance purposes. Inspection of the drains should be carried out regularly to avoid waterlogging of the garden and the subsequent increase in dead weight load. Where there is a run-off from a large sill or gully onto the roof surface, the build-up of silt may allow the germination of seeds, therefore this type of detail should be avoided. Any growth occurring will be restricted and will not normally affect the performance of the roof and will be no worse than that occurring on normal flat roofs.

## Indications and Important Recommendations

- In case of new construction and renovation, possible chemical incompatibilities with APP plastomer-modified bitumen sheets shall be taken into account.
- In case of refurbishment, chemical incompatibilities with old waterproofing systems consisting of PVC membranes, modified tar-based mastics or any other, shall be taken into account, and it may be necessary to remove them completely or to use suitable separating layers.
- If it is necessary to adhere to metallic or slightly porous elements, a bituminous primer (IMPRIDAN 100) shall be applied to the entire surface to be welded beforehand.
- This product may form part of a waterproofing system, so all the documents referred to in the Danosa Solutions Manual must be taken into account, as well as all the regulations and legislation

that must be complied with in this respect.

- There is no chemical incompatibility between the Danosa range of SBS elastomeric bitumen and APP plastomeric bitumen membranes.
- Not suitable as cap sheet on green roofs; use GARDEN variant.
- Possible incompatibility between thermal insulation and waterproofing shall be checked.
- A separating layer (DANOFELT or DANODREN) shall be laid before laying the heavy protection (paving, gravel, topsoil, etc).
- Special attention must be paid to the execution of the singular points, such as parapets (meetings with vertical and emergent elements), drains, expansion joints, etc.
- Polyurethane foam shall not be sprayed directly on top of the waterproofing without the use of a suitable separating layer (geotextiles, mortar layers, polyethylene film, etc).
- If expansion that could affect the sheet is expected, a geotextile separating layer (Danofelt PY 200) shall be used between the sheet and the extruded polystyrene insulation panels, so that each product expands independently.
- NOTE: For more information on the Danosa systems in which this product is used, please see the document "Waterproofing Solutions".

## **Maintenance Recommendations**

- Please refer to DANOSA UK Technical Statement 'Flat Roof Waterproofing – Cleaning and Maintenance Recommendations'

## **Handling, storage and preservation**

- Before moving the pallet, check the condition of the shrink-wrap and reinforce if necessary.
- The product must be stored in a dry place protected from rain, sun, heat and low temperatures.
- The product must be stored in an upright position.
- The product will be used on a first-come, first-served basis.
- This product should not be installed when the temperature is below -5°C.
- This product is not toxic or flammable.
- Waterproofing work must not be carried out when weather conditions may be detrimental, in particular when it is snowing or there is snow or ice on the roof, when it is raining or the roof is wet, surface dampness >8% according to NTE QAT, or when a strong wind is blowing.
- Pallets shall not be stacked on top of each other.
- For high storage, the racks must have three cross members, or braces under the wooden pallet skids.
- For handling with a crane, use a protective net as indicated on the pallet label.
- Danosa recommends consulting the safety data sheet for this product, which is permanently available at [danosa.com](http://danosa.com), Knowledge Portal, or it can be requested from our Technical Department.
- In all cases, the Occupational Safety and Hygiene standards, as well as the standards of good construction practice, must be taken into account.
- For further information, please contact our Technical Department.

## **Notice**

- The information contained in this document and any other advice provided, are given in good faith, based on DANOSA's current knowledge and experience when products are properly stored, handled and applied, in normal situations and in accordance with the recommendations of DANOSA. The information applies only to the application (s) and the product (s) to which reference is expressly made. In case of changes in the parameters of the application, or in case of a different application, consult the DANOSA Technical Service before using the DANOSA products. The information

contained herein does not exonerate the responsibility of the building agents to test the products for the application and intended use, as well as their correct application in accordance with current legal regulations. The product images used in our communications are indicative and may differ slightly in color and aesthetic appearance in relation to the final product. Orders are accepted in accordance with the terms of our current General Sales Conditions. DANOSA reserves the right to modify, without prior notice, the data reflected in this documentation. Website: **www.danosa.com** E-mail: **info@danosa.com** Telephone: **+34 949 88 82 10**