

## **POLYDAN PLUS FM 180-60/GP FRBR ELAST**

Waterproofing sheet of SBS modified bitumen with mineral self-protection.



BBA 10/4787 (1)



ETE 06/0058

POLYDAN PLUS F.M 180-60/GP FRBR ELAST. is a waterproofing bituminous sheet with self-protected surface of 5.6 kg/m<sup>2</sup>. Composed of a reinforced and stabilized polyester felt reinforcement, covered on both sides with SBS modified bitumen mastic. On the upper side of the sheet, slate in grey (black) colour is used as protective material. The anti-adhesive material used on the lower side is polyethylene film.

### **Presentation**

- Length (cm): 800
- Width (cm): 100
- Thickness (mm): 4.0
- Product code: 141926

### **Technical Data**

<b>Concept</b>	<b>Value</b>	<b>Standard</b>
External fire behaviour	Broof(t1)	UNE-EN 1187
Durability flexibility	-5 ± 5	-
Creep durability (°C)	100 ±10	UN-EN 1110
Elongation at break longitudinal (%)	45 ±15	UNE-EN 12311-1
Elongation at transverse break (%)	45 ±15	-
Humidity resistance factor	>20.000	UNE-EN 1931
Low temperature flexibility (°C)	<-15	UNE-EN 1109

Concept	Value	Standard
Mass per unit area (nominal) (kg/m <sup>2</sup> )	5.6	-
Reaction to fire	E	UNE-EN 11925-2; UNE-EN 13501-1
Resistance to static loading (kg)	>20	UNE-EN 12730
Resistencia a la difusión (GPa.s.m <sup>2</sup> /kg)	400 ± 50	-
Resistance to root penetration	No pasa	UNE-EN 13948
Longitudinal tensile strength (N / 5cm)	900 ± 250	-
Transverse tensile strength (N / 5cm)	650 ± 250	-
Longitudinal resistance to tearing (nail shank) (N)	280 ± 30	-
Transversal resistance to tearing (nail shank) (N)	320 ± 20	-
Hazardous substances	PND	-

## Additional Technical Data

Concept	Value	Standard
Adhesion of granules (%)	<30	UNE-EN 12039
Dimensional stability at elevated temperatures (longitudinal) (%)	<0.3	UNE-EN 1107-1
Dimensional stability at high temperatures (transversal) (%)	<0.3	-
Creep resistance at high temperatures (°C)	>100	UN-EN 1110

## Environmental Information

Concept	Value	Standard
Recycled content afterword the consumer (%)	35	-
Manufactured in	Fontanar - Guadalajara (España)	-

## Instruction for Use

1. First of all, center the plinth on the deck ceiling opening.
2. Fix the plinth to the deck with steel lag screws:
  - Three units per meter on the plinth's perimeter heel.
  - Over concrete slab supports, domes will be installed with concrete screws, washers and Ø6mm lag screws.
  - Over steel deck systems with thermal insulation and waterproofing membrane, domes will be installed with steel screws directly to the structure.
  - If the skylight has to be placed before the steel deck, an auxiliary frame welded to the main structure will be required.

3. Install the waterproofing membrane covering the exterior plinth surface.
4. Remove the dome's protector film. Place the inferior dome over the plinth and over the.
5. Place the inferior dome over the plinth structure and install the self-adhesive washers on the inferior dome top surface, matching them with spaces to be drilled. Screw the top methacrylate dome, finishing the whole skylight. Do not tight screws in excess, because:

- Domes could be broken.
  - Expansion joint effect will be nullified.
6. Place finish caps over the screws.

**IMPORTANT:** Do not install the dome until plinth has been placed in order to avoid any stain related to waterproofing works.